



# Seal & Bond Sealtrans Ramen en Deuren

FLEXIBLE, DECORATIVE PUTTY

- ✓ Elastic bonding and sealing.
- ✓ Contains no plasticisers

## Technical Info

- Base: neutral silicone.
- Odor: neutral.
- Shore-A hardness (DIN 53505): 24.
- Modulus by 100% elasticity (DIN53504): 0,37 N/mm<sup>2</sup>.
- Elongation at break (DIN 53504): 900%.
- Elastic recovery: >70%.
- Tensile strength (DIN53504): 1,40 N/mm<sup>2</sup>.
- Movement capacity: 25%.
- Consistency (ISO 7390): stable till <2mm.
- Curing: in contact with air humidity.
- Application temperature: between +5°C and +40°C.
- Skin cure (at 23°C and 55% R.H.): 20-25min.
- Full cure time (at 23°C and 55%R.H.): 3 mm in 24h.
- Volume shrinkage after curing (DIN EN ISO 10563): 0%.
- Paintable: no.
- Density at 23° and 50% R.H. 1,03 g/ml.
- Thermal stability (fully cured): from -60°C up to +155°C ( peak +180°C).
- Frost resistance: till -15°C during transport.
- Shelf life: 18 months, kept dry and cool in closed original packing.
- Safety measures: Please consult the safety data sheet.

## Product [STS R&D]

### Characteristics

Synthetic rubber polymer based on pigmented siloxanes with good adhesion to metal, aluminium, galvanisation, polyester, wood, concrete complex, glass, most rubbers and plastics, natural stone (does not bleed through), brick, concrete, acrylic, ceramics, both mutually and in combination. Good adhesion to painted or powder-coated surfaces. Unlike previous generations of silicone products, Sealtrans is free of known toxic or harmful substances and is entirely MEKO-free.

## Packing

Seal & Bond Sealtrans Ramen en Deuren black - cartridge 310ml	539016116
Seal & Bond Sealtrans Ramen en Deuren transparent - cartridge 310ml	539096116

## Use

- Apply to clean and dry substrates, above 5°C.
- Finish seams with Novatio Seal & Bond Finisher. Use Seal & Bond Special Primer on PE, PP, Teflon and polyolefin. Not paintable.